

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/Acid RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3746 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844/4850 Polyaspartic
Acetaldehyde	TS	NR		TS	TS	TS			SD	OK	SD	OK	TS	TS	TS	SD	TS
Acetic Acid - 10%	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Acetic Acid - 10-50%	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Acetic Acid 50% to Glacial (100%)	SD	SD		TS	SD	SD			NR	SD	NR	SD	SD	SD	SD	SD	SD
Acetic Anhydride	TS	NR		TS	TS	TS			NR	SD	NR	SD	TS	TS	SD	SD	SD
Acetone - 10%	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Acetone - 100%	SD	NR		SD	SD	SD			SD	SD	SD	SD	SD	SD	SD	SD	SD
Acetyl Chloride - 100%	TS	NR		TS	TS	TS			NR	OK	NR	OK	TS	TS	TS	SD	TS
Acrylic Acid - 100%	TS	NR		TS	TS	TS			SD	OK	SD	OK	TS	TS	TS	SD	TS
Acrylonitrile*	NR	NR		NR	NR	NR			NR	SD	NR	SD	NR	NR	NR	NR	NR
Adipic Acid - 25%	OK	OK		TS	OK	OK			OK	OK	OK	OK	OK	OK	SD	SD	SD
Allyl Alcohol	OK	NR		SD	SD	NR			SD	OK	SD	OK	OK	OK	SD	SD	SD
Allyl Chloride	TS	NR		TS	TS	TS			TS	OK	TS	OK	TS	TS	NR	NR	NR
Alum (Saturated Solution)	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	TS	OK	TS
Aluminum Bromide	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Aluminum Chloride	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Aluminum Nitrate (Saturated)	TS	NR		TS	TS	TS			SD	OK	SD	OK	TS	TS	OK	OK	OK
Aluminum Sulfate	TS	NR		TS	TS	TS			SD	OK	SD	OK	TS	TS	OK	OK	OK
Ammonia (Wet Gas)	OK	OK		OK	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Ammonium Bisulfite	TS	NR		OK	TS	TS			SD	OK	SD	OK	TS	TS	OK	OK	OK
Ammonium Chloride	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Ammonium Cocoampholyte - 30%	OK	OK		SD	OK	OK			TS	OK	TS	OK	OK	OK	OK	OK	OK
Ammonium Fluoride	TS	NR		TS	TS	TS			TS	OK	TS	OK	TS	TS	OK	OK	OK
Ammonium Hydroxide - 20%	OK	OK		OK	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Ammonium Hydroxide - 38%	OK	OK		OK	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK
Ammonium Lauryl Sulfate - 30%	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Ammonium Nitrate	SD	SD		TS	SD	SD			OK	OK	OK	OK	SD	SD	OK	OK	OK
Ammonium Persulfate	SD	SD		TS	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD
Ammonium Sulfate	SD	SD		TS	SD	SD			OK	TS	OK	TS	SD	SD	SD	OK	SD
Ammonium Sulfide	SD	SD		TS	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD
Ammonium Sulfite	SD	SD		TS	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD
Ammonium Xylene Sulfonate - 40%	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Amyl Acetate	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Amyl Alcohol	SD	NR		TS	SD	SD			TS	TS	TS	TS	SD	SD	SD	NR	SD
Aniline	NR	NR		NR	NR	NR			NR	OK	NR	OK	NR	NR	NR	SD	NR
Aniline Hydrochloride	OK	NR		TS	OK	OK			TS	SD	TS	SD	OK	OK	TS	NR	TS
Antimony Chloride (tri)	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	TS	OK	TS
Aqua Regia	SD	SD		TS	SD	SD			NR	OK	NR	OK	SD	SD	SD	OK	SD
Arsenous Acid	SD	SD		TS	SD	SD			TS	SD	TS	SD	SD	SD	SD	SD	SD
Barium Chloride	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	SD	SD
Barium Hydroxide	OK	OK		OK	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Barium Sulfate	OK	OK		OK	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Barium Sulfide	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Beer	NR	OK		SD	NR	NR			TS	OK	TS	OK	NR	NR	TS	OK	TS

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	TPM #115-SA/U1/U4	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/Acid RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Benzal Chloride	SD	NR	TS	SD	SD			OK	NR	OK	NR	SD	SD	SD	NR	SD		
Benzaldehyde	NR	NR	TS	NR	NR			OK	OK	OK	OK	NR	NR	SD	SD	SD		
Benzene (Benzol)	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD		
Benzene Sulfonic Acid 50-100%	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	TS	SD	TS		
Benzene Thiol	SD	SD	TS	SD	SD			NR	OK	NR	OK	SD	SD	TS	SD	TS		
Benzyl Alcohol	TS	NR	SD	TS	TS			SD	OK	SD	OK	TS	TS	TS	SD	TS		
Benzoic Acid (Saturated)	OK	SD	SD	OK	OK			TS	OK	TS	OK	OK	OK	SD	SD	SD		
Benzoyl Chloride	TS	NR	TS	TS	TS			TS	OK	TS	OK	TS	TS	TS	OK	TS		
Benzyl Chloride	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	TS	SD	TS		
Black Liquor (Paper)	SD	SD	SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD		
Bleach - 5%	OK	OK	SD	OK	OK			SD	OK	SD	OK	OK	OK	SD	OK	SD		
Boric Acid (Saturated)	OK	OK	SD	OK	OK			TS	OK	TS	OK	OK	OK	SD	OK	SD		
Brake Fluid	NR	OK	TS	NR	NR			NR	OK	NR	OK	NR	NR	SD	OK	SD		
Brine	OK	OK	SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK		
Bromine, Wet Gas	NR	NR	TS	NR	NR			TS	OK	TS	OK	NR	NR	SD	SD	SD		
Bromine, Dry Gas	NR	NR	TS	NR	NR			TS	SD	TS	SD	NR	NR	SD	SD	SD		
Bromine Water - 5%	NR	NR	TS	NR	NR			TS	OK	TS	OK	NR	NR	TS	SD	TS		
Butanol Normal	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	TS	OK	TS		
Butyl Acetate	SD	SD	SD	SD	SD			SD	SD	SD	SD	SD	SD	SD	SD	SD		
Butyl Acrylate	SD	NR	SD	NR	NR			NR	OK	SD	OK	SD	SD	TS	SD	TS		
Butyl Amine	SD	NR	SD	NR	NR			NR	OK	NR	OK	SD	SD	SD	SD	SD		
Butyl Carbitol	TS	NR	TS	TS	TS			NR	TS	NR	TS	TS	TS	TS	SD	TS		
Butyl Carbitol Acetate	TS	NR	TS	TS	TS			NR	OK	NR	OK	TS	TS	TS	SD	TS		
Butyl Cellosolve	TS	NR	TS	TS	TS			NR	OK	NR	OK	TS	TS	TS	SD	TS		
Butyl Cellosolve Acetate	NR	NR	TS	NR	NR			NR	SD	NR	SD	NR	NR	SD	SD	SD		
Butyl Ether	SD	SD	SD	SD	SD			SD	SD	SD	SD	SD	SD	SD	SD	SD		
Butyl Acid Levulinic	SD	SD	SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD		
Butyric Acid - 100%	SD	SD	TS	SD	SD			NR	OK	NR	OK	SD	SD	SD	SD	SD		
Cadmium Chloride	SD	SD	SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD		
Cadmium Plating - Cyanide	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD		
Calcium Bisulfite	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD		
Calcium Chloride	OK	OK	SD	OK	OK			SD	OK	SD	OK	OK	OK	SD	OK	SD		
Calcium Hydroxide	OK	OK	SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD		
Calcium Hypochlorite - 5%	SD	SD	SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD		
Calcium Nitrate	OK	OK	SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK		
Calcium Sulfate	OK	OK	SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK		
Calcium Sulfite	SD	SD	SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	SD	OK		
Caprylic Acid (Octanoic Acid )	TS	NR	TS	TS	TS			TS	OK	TS	OK	TS	TS	OK	SD	OK		
Carbolic Acid (Phenol) - 88%	TS	NR	TS	TS	TS			NR	OK	NR	OK	TS	TS	TS	NR	TS		
Carbon Bisulfide (Di) Fumes (Wet)	NR	NR	TS	NR	NR			SD	TS	SD	TS	NR	NR	TS	SD	TS		
Carbon Dioxide Gas	OK	OK	SD	OK	OK			TS	SD	TS	SD	OK	OK	SD	OK	SD		
Carbon Tetrachloride	SD	NR	SD	SD	NR			SD	OK	SD	OK	SD	SD	OK	OK	OK		
Castor Oil	OK	OK	SD	OK	OK			OK	SD	OK	SD	OK	OK	OK	SD	OK		
Cellosolve	SD	SD	TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD		

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/Acid RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Cellosolve Acetate	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Chloroacetic Acid - 1-20%	NR	NR		TS	NR	NR			SD	OK	SD	OK	NR	NR	TS	SD	TS
Chloroacetic Acid - 20-50%	NR	NR		TS	NR	NR			NR	SD	NR	SD	NR	NR	TS	NR	TS
Chloroacetic Acid - 50-100%	NR	NR		TS	NR	NR			NR	SD	NR	SD	NR	NR	TS	NR	TS
Chlorine Dioxide Solution	TS	NR		TS	TS	TS			NR	TS	NR	TS	TS	TS	TS	OK	TS
Chlorine Gas - Dry	OK	SD		SD	OK	OK			NR	SD	NR	SD	OK	OK	SD	SD	SD
Chlorine Gas - Wet	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	SD	TS
Chlorine Water - Saturated	NR	NR		SD	NR	NR			TS	OK	TS	OK	NR	NR	TS	SD	TS
Chlorobenzene (Mono)	SD	SD		TS	SD	SD			OK	OK	OK	OK	SD	SD	SD	SD	SD
Chlorobutane	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	SD	SD	SD
Chloroform	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	SD	TS
Chlorophenol	SD	SD		SD	SD	SD			NR	SD	NR	SD	SD	SD	TS	SD	TS
Chlorosulfonic Acid	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	SD	TS
Chlorotoluene	NR	NR		TS	NR	NR			SD	SD	SD	SD	NR	NR	TS	SD	TS
Chromic Acid - 10%	SD	SD		SD	SD	SD			SD	SD	SD	SD	SD	SD	SD	OK	SD
Chrome Plating 20-48 oz/gal	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	SD	OK	SD
Chromic Chloride	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Citric Acid	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Copper Chloride	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK
Copper Nitrate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	SD	OK
Copper Plating - Cyanide	SD	SD		SD	SD	SD			SD	TS	SD	TS	SD	SD	OK	SD	OK
Copper Plating - Acid	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	OK	SD	OK
Copper Sulfate	TS	NR		TS	TS	TS			TS	OK	TS	OK	TS	TS	OK	TS	OK
Corn Oil	SD	OK		SD	NR	NR			SD	OK	SD	OK	SD	SD	SD	SD	SD
Cottonseed Oil	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Cresol (Cresylic Acid )	NR	SD		NR	NR	NR			NR	SD	NR	SD	NR	NR	SD	SD	SD
Cresylic Acid	NR	NR		NR	NR	NR			NR	SD	NR	SD	NR	NR	SD	SD	SD
Cumene	SD	SD		SD	SD	SD			NR	OK	NR	OK	SD	SD	SD	OK	SD
Cyclohexane	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Cyclohexanone	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Cymene	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Dextrose	SD	OK		SD	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD
Dibromopropane Phosphate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Dibutyl Phthalate	OK	SD		TS	OK	OK			TS	OK	TS	OK	OK	OK	OK	SD	OK
Dichloro Acetic Acid - 20%	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	SD	TS
Diethanolamine	SD	SD		TS	SD	SD			NR	OK	NR	OK	SD	SD	TS	SD	TS
Diethylene Chloroformate	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	TS	SD	TS
Diethylketone - 100%	NR	NR		TS	NR	NR			SD	SD	SD	SD	NR	NR	TS	SD	TS
Dimethylaminopropylamine	NR	NR		NR	NR	NR			NR	SD	NR	SD	NR	NR	SD	SD	SD
Dimethyl Aniline	NR	NR		NR	NR	NR			NR	SD	NR	SD	NR	NR	NR	SD	NR
Dimethyl Carbamoyl Chloride	NR	NR		TS	NR	NR			SD	SD	SD	SD	NR	NR	SD	SD	SD
Dimethyl Carbonyl Chloride	SD	NR		NR	NR	NR			NR	SD	NR	SD	SD	SD	NR	SD	NR
Dimethyl Formamide	NR	NR		NR	NR	NR			SD	SD	NR	SD	NR	NR	NR	NR	NR
Dimethyl Sulfoxide	SD	SD		TS	SD	SD			TS	SD	TS	SD	SD	SD	TS	SD	TS

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/Acid RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Dinitro Benzene	SD	SD		TS	SD	SD			SD	SD	SD	SD	SD	SD	TS	SD	TS
Dinitro Toluene	SD	SD		TS	SD	SD			SD	SD	SD	SD	SD	SD	TS	SD	TS
Dodecyl Alcohol (Lauryl)	SD	SD		TS	SD	SD			SD	SD	SD	SD	SD	SD	SD	SD	SD
Ethoxy Ethanol	SD	NR		TS	NR	NR			SD	OK	SD	OK	SD	SD	SD	SD	SD
Ethoxylated Nonyl Phenol	SD	SD		SD	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD
Ethyl Acetate	NR	SD		TS	NR	NR			SD	OK	SD	OK	NR	NR	TS	SD	TS
Ethyl Acrylate	NR	NR		TS	NR	NR			TS	OK	TS	OK	NR	NR	TS	SD	TS
Ethyl Alcohol	SD	NR		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	NR	SD
Ethylamine	NR	NR		TS	NR	NR			NR	SD	NR	SD	NR	NR	TS	NR	TS
Ethyl Bromide	TS	NR		TS	TS	TS			NR	OK	NR	OK	TS	TS	TS	NR	TS
Ethyl Chloride	SD	SD		TS	SD	SD			NR	SD	NR	SD	SD	SD	TS	SD	TS
Ethyl Chloroformate	SD	SD		TS	SD	SD			SD	SD	SD	SD	SD	SD	TS	SD	TS
Ethyl Ether	NR	SD		SD	NR	NR			SD	SD	SD	SD	NR	NR	SD	SD	SD
Ethyl Hexyl Acrylate	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	SD	SD	SD
Ethylene Dichloride	NR	NR		TS	NR	NR			NR	SD	NR	SD	NR	NR	TS	SD	TS
Ethylene Glycol	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Ethylene Oxide (Dilute)	NR	SD		SD	NR	NR			TS	SD	TS	SD	NR	NR	OK	SD	OK
Ethyl Sulfate	SD	NR		SD	NR	NR			TS	OK	NR	OK	SD	SD	SD	OK	SD
Ferric Chloride	SD	SD		TS	SD	SD			SD	SD	SD	SD	SD	SD	SD	OK	SD
Ferric Nitrate	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Ferric Sulfate	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Fluosilicic Acid - 25%	NR	NR		TS	NR	NR			TS	OK	TS	OK	NR	NR	TS	NR	TS
Formaldehyde	OK	SD		TS	OK	OK			SD	OK	SD	OK	OK	OK	SD	OK	SD
Formic Acid	SD	SD		TS	SD	SD			SD	TS	SD	TS	SD	SD	SD	OK	SD
Furfural to 10%	SD	SD		TS	SD	SD			TS	TS	TS	TS	SD	SD	SD	OK	SD
Gasoline	SD	OK		SD	SD	SD		OK	SD	SD	SD	SD	SD	SD	SD	OK	SD
Aviation	SD	OK		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Diesel	SD	OK		TS	SD	SD		OK	SD	OK	SD	OK	SD	SD	SD	OK	SD
Jet Fuel	SD	OK		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Premium Unleaded	SD	OK		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Unleaded	SD	OK		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Glucose	TS	OK		SD	TS	TS			OK	OK	OK	OK	TS	TS	OK	TS	OK
Glycerine	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Glycolic Acid to 70%	SD	SD		SD	SD	SD			SD	TS	SD	TS	SD	SD	OK	OK	OK
Gold Plating (Cyanide)	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	OK	SD	OK
Grape Juice	TS	OK		SD	TS	TS			TS	OK	TS	OK	TS	TS	TS	TS	TS
Green Liquor (Paper Industry)	SD	SD		SD	SD	SD			SD	TS	SD	TS	SD	SD	OK	OK	OK
Heptane	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Hexane	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Hydrazine - 35%	SD	NR		NR	NR	NR			NR	OK	SD	OK	SD	SD	SD	SD	SD
Hydrazine Hydrate	NR	NR		NR	NR	NR			NR	OK	SD	OK	NR	NR	SD	SD	SD
Hydriodic Acid - 20%	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	SD	OK	SD
Hydrobromic Acid - 20%	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	SD	OK	SD
Hydrobromic Acid - 48%	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	SD	OK	SD

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/ACID RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Hydrochloric Acid - 10%	SD	SD		SD	SD	SD			OK	SD	OK	SD	SD	SD	SD	OK	SD
Hydrochloric Acid - 20%	SD	SD		TS	SD	SD			OK	SD	OK	SD	SD	SD	SD	OK	SD
Hydrochloric Acid - 37%	SD	NR		TS	SD	SD			NR	SD	OK	SD	SD	SD	SD	OK	SD
Hydrofluoric Acid - 1-10% *	OK	NR		TS	OK	OK			NR	OK	NR	OK	OK	OK	SD	OK	SD
Hydrofluoric Acid - 20% *	SD	NR		TS	SD	SD			NR	OK	NR	OK	SD	SD	TS	SD	TS
Hydrofluoric Acid - 21-48%	NR	NR		NR	NR	NR			NR	OK	NR	OK	NR	NR	SD	SD	SD
Hydrofluosilicic Acid - 10%	NR	NR		TS	NR	NR			TS	OK	TS	OK	NR	NR	TS	NR	TS
Hydrofluosilicic Acid - 35%	NR	NR		TS	NR	NR			TS	OK	TS	OK	NR	NR	TS	NR	TS
Hydrogen Peroxide - 30%	NR	NR		NR	NR	NR			NR	OK	NR	OK	NR	NR	SD	SD	SD
Hydrogen Sulfide Gas	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	SD	SD	SD
Hypo (Photographic Solution)	SD	SD		SD	SD	SD			SD	SD	SD	SD	SD	SD	OK	OK	OK
Hypochlorous Acid	NR	NR		NR	NR	NR			NR	NR	NR	NR	NR	NR	NR	NR	NR
Iodine, Chrystals and Vapor	SD	SD		NR	NR	NR			SD	SD	NR	SD	SD	SD	OK	OK	OK
Isocetylthioglycolate	SD	SD		SD	SD	SD			SD	SD	TS	SD	SD	SD	SD	OK	SD
Isophorone	NR	NR		NR	NR	NR			NR	NR	NR	NR	NR	NR	NR	SD	NR
Isopropyl Acetate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Isopropyl Alcohol	SD	SD		SD	SD	SD		OK	SD	OK	SD	OK	SD	SD	SD	OK	SD
Isopropyl Ether	SD	SD		NR	SD	NR			NR	SD	NR	SD	SD	SD	SD	OK	SD
Jet Fuel JP-4	OK	OK		SD	OK	OK			SD	SD	SD	SD	OK	OK	SD	OK	SD
Kerosene	OK	OK		SD	OK	OK		OK	SD	OK	SD	OK	OK	OK	SD	OK	SD
Ketchup	TS	OK		OK	SD	SD			SD	OK	SD	OK	TS	TS	TS	TS	TS
Lactic Acid Concentrated	NR	SD		SD	SD	SD		OK	SD	OK	NR	OK	NR	NR	SD	OK	SD
Lard	TS	OK		SD	TS	TS			TS	OK	TS	OK	TS	TS	OK	TS	OK
Lauric Acid	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Lauryl Chloride	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	OK	OK	OK
Lead Acetate	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK
Lecithin	OK	OK		SD	OK	OK			OK	TS	OK	TS	OK	OK	OK	OK	OK
Levulinic Acid (Saturated)	OK	OK		SD	OK	OK			SD	SD	SD	SD	OK	OK	OK	OK	OK
Linseed Oil	OK	OK		SD	OK	OK			SD	TS	SD	TS	OK	OK	OK	OK	OK
Lithium Hydroxide - 10%	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD
Lithium Hydroxide (Saturated)	SD	SD		SD	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD
Maleic Acid	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Malic Acid	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK
Mercury and Salts	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK
Methanol - 100%	OK	SD		SD	SD	NR		OK	SD	OK	NR	OK	OK	OK	SD	SD	SD
Methyl Acetate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Methylamyl Alcohol	NR	NR		TS	NR	NR			TS	OK	TS	OK	NR	NR	SD	SD	SD
Methylene Chloride	NR	NR		NR	NR	NR			NR	SD	NR	SD	NR	NR	NR	SD	NR
Methyl Chloride	NR	NR		NR	NR	NR			NR	SD	NR	SD	NR	NR	NR	SD	NR
Methyl-Ethyl Ketone	SD	SD		NR	SD	SD		OK	SD	OK	SD	OK	SD	SD	SD	OK	SD
Methyl Oleate	SD	SD		SD	SD	SD			OK	SD	OK	SD	SD	SD	OK	OK	OK
Methyl Isobutyl Ketone	NR	NR		NR	NR	NR			SD	OK	NR	OK	NR	NR	SD	OK	SD
Milk - Fresh and Sour	TS	OK		SD	TS	TS		OK	TS	SD	TS	SD	TS	TS	TS	TS	TS
Mineral Spirits	OK	OK		SD	OK	OK		OK	SD	SD	SD	SD	OK	OK	SD	OK	SD

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/ACID RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Molasses	TS	OK		OK	TS	TS			TS	SD	TS	SD	TS	TS	TS	TS	TS
Muratic Acid	OK	OK		SD	OK	OK			SD	SD	SD	SD	OK	OK	OK	OK	OK
Naphtha - Aliphatic	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Naphtha - Aromatic (Coal Tar)	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Naphthalene (In Benzene)	TS	NR		TS	TS	TS			SD	TS	SD	TS	TS	TS	TS	SD	TS
Naphthenic Acid	NR	NR		NR	NR	NR			NR	OK	NR	OK	NR	NR	SD	OK	SD
Nickel Plating, Bright	OK	OK		TS	OK	OK			SD	OK	SD	OK	OK	OK	OK	SD	OK
Nitric Acid - 5%	SD	OK		TS	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Nitric Acid - 10%	SD	SD		TS	SD	SD		OK	SD	OK	SD	OK	SD	SD	SD	SD	SD
Nitric Acid - 25%	NR	NR		TS	NR	NR			SD	OK	SD	OK	SD	SD	TS	TS	TS
Nitric Acid - 40%	NR	NR		TS	NR	NR			NR	OK	NR	OK	SD	SD	TS	TS	TS
Nitric Acid - 60%	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	TS	TS
Nitric Acid - 73%	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	SD	TS
Nitric Acid - 89%	NR	NR		TS	NR	NR			NR	NR	NR	NR	NR	NR	TS	SD	TS
Nitrioltriethanol	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	TS	SD	TS
Nitrobenzene	NR	NR		TS	NR	NR			SD	OK	SD	OK	NR	NR	TS	SD	TS
Nitromethane	NR	NR		TS	NR	NR			SD	OK	SD	OK	NR	NR	TS	SD	TS
Octanol	SD	SD		TS	SD	SD			SD	SD	SD	SD	SD	SD	OK	SD	OK
Oils	OK	OK		SD	OK	OK			SD	NR	SD	NR	OK	OK	OK	OK	OK
Sour Crude Petroleum	SD	OK		SD	SD	SD			SD	NR	SD	NR	SD	SD	OK	OK	OK
Animal	NR	OK		SD	NR	NR			SD	NR	SD	NR	NR	NR	OK	OK	OK
Mineral	NR	OK		SD	NR	NR			SD	SD	SD	SD	NR	NR	OK	OK	OK
Vegetable	NR	OK		SD	NR	NR			TS	SD	TS	SD	NR	NR	TS	TS	TS
Oleic Acid	SD	SD		SD	SD	SD			TS	SD	TS	SD	SD	SD	OK	OK	OK
Oxalic Acid (Saturated)	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK
Para Xylene	SD	NR		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD
Pelargonic Acid	OK	OK		TS	OK	OK			TS	OK	TS	OK	OK	OK	SD	OK	SD
Pentachloroethane	SD	SD		SD	SD	SD			TS	TS	TS	TS	SD	SD	SD	OK	SD
Perchloric Acid - 30%	SD	SD		TS	SD	SD			NR	TS	NR	TS	SD	SD	TS	SD	TS
Perchloroethylene	SD	SD		TS	SD	SD			NR	SD	NR	SD	TS	TS	TS	SD	TS
Phenol - 5%	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	TS	SD	TS
Phenol - 85%	NR	NR		TS	NR	NR			NR	TS	NR	TS	NR	NR	TS	SD	TS
Phenol Sulfonic Acid - 65%	SD	NR		NR	NR	NR			NR	OK	NR	OK	SD	SD	SD	OK	SD
Phosphoric Acid - 20%	SD	OK		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD
Phosphoric Acid - 50%	SD	OK		NR	SD	SD		OK	SD	OK	SD	OK	SD	SD	SD	OK	SD
Phosphoric Acid - 85%	SD	NR		NR	SD	SD			NR	OK	NR	OK	SD	SD	SD	SD	SD
Phosphorous Oxychloride	NR	NR		TS	NR	NR			SD	OK	SD	OK	NR	NR	TS	SD	TS
Phosphorous Trichloride	NR	NR		TS	NR	NR			SD	SD	SD	SD	NR	NR	TS	SD	TS
Picric Acid - 10% (In Alcohol) *	NR	NR		TS	NR	NR			TS	SD	TS	SD	NR	NR	TS	SD	TS
Polyacrylic Acid - 50%	OK	OK		SD	OK	OK			TS	SD	TS	SD	OK	OK	OK	OK	OK
Potassium Acetate	OK	SD		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK
Potassium Bichromate	NR	SD		SD	NR	NR			OK	SD	OK	SD	NR	NR	OK	OK	OK
Potassium Bromide	SD	SD		SD	SD	SD			OK	SD	OK	SD	SD	SD	OK	OK	OK
Potassium Carbonate - 25%	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	TPM #115-S4/U1/U4	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/Acid RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Potassium Chlorate	SD	OK		SD	SD	SD			OK	OK	OK	OK	SD	SD	OK	OK	OK	
Potassium Chloride	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Potassium Cyanide	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK	
Potassium Fluoride	OK	OK		SD	OK	OK			TS	SD	TS	SD	OK	OK	OK	OK	OK	
Potassium Hydroxide - 10%	OK	OK		SD	OK	OK			OK	SD	OK	SD	OK	OK	OK	OK	OK	
Potassium Hydroxide - 50%	SD	OK		SD	SD	SD			OK	SD	OK	SD	SD	SD	OK	OK	OK	
Potassium Nitrate	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Potassium Permanganate	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	SD	SD	SD	
Potassium Persulfate	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	OK	OK	OK	
Potassium Sulfate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK	
Propanediol	OK	SD		TS	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Propionic Acid - 100%	NR	NR		TS	NR	NR			SD	OK	SD	OK	NR	NR	TS	NR	TS	
Propylene Glycol	SD	SD		TS	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD	
Pyridine	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	SD	SD	SD	
Rayon Spin Liquor	SD	SD		SD	SD	SD			NR	OK	NR	OK	SD	SD	SD	OK	SD	
Salicylaldehyde	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD	
Salicylic Acid	SD	SD		SD	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD	
Salt Brine	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	SD	OK	SD	
Silicon Tetrachloride	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	SD	OK	SD	
Silver Nitrate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	SD	SD	SD	
Skydrol	SD	SD		TS	SD	SD			NR	OK	NR	OK	SD	SD	SD	SD	SD	
Sodium Acetate	SD	SD		SD	SD	SD			OK	OK	OK	OK	SD	SD	OK	OK	OK	
Sodium Bicarbonate	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Bisulfate	OK	OK		SD	OK	OK			OK	SD	OK	SD	OK	OK	OK	OK	OK	
Sodium Bisulfite	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Bromate	OK	OK		SD	OK	OK			OK	TS	OK	TS	OK	OK	OK	OK	OK	
Sodium Carbonate (Saturated)	OK	OK		SD	OK	OK			OK	NR	OK	NR	OK	OK	OK	OK	OK	
Sodium Chloride	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Chlorite (Saturated)	SD	SD		TS	SD	SD			TS	OK	TS	OK	SD	SD	SD	SD	SD	
Sodium Chromate	OK	OK		SD	OK	OK			SD	OK	SD	OK	OK	OK	OK	OK	OK	
Sodium Chlorate	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Cyanide - 15%	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Dichromate	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	OK	OK	
Sodium Fluoride	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	OK	OK	OK	
Sodium Hydrosulfide - 45%	SD	SD		SD	SD	SD			SD	OK	SD	OK	SD	SD	OK	SD	OK	
Sodium Hydroxide - 10%	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Hydroxide - 50%	SD	OK		SD	SD	SD		OK	OK	OK	OK	OK	SD	SD	OK	OK	OK	
Sodium Hypochlorite - 3%	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	SD	OK	SD	
Sodium Hypochlorite - 17%	NR	SD		NR	NR	NR			NR	OK	NR	OK	NR	NR	SD	SD	SD	
Sodium Lauryl Sulfate - 20%	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD	
Sodium Oxalate	OK	OK		TS	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Peroxide - Peroxide Bleach	SD	SD		SD	SD	SD			OK	OK	OK	OK	SD	SD	SD	OK	SD	
Sodium (Acid) Phosphate	SD	SD		TS	SD	SD			SD	OK	SD	OK	SD	SD	SD	OK	SD	
Sodium Phosphate (Tri)	OK	OK		SD	OK	OK			OK	OK	OK	OK	OK	OK	OK	OK	OK	

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department

**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS	TPM #115-S4/U1/U4	FasTop (No Topcoat)	SLURRY SYSTEMS	TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554	EPOXY / POLYURETHANE COATINGS	4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/ACID RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Sodium Polymethacrylate	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Sodium Sulfate	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Sodium Sulfide (Saturated)	NR	SD	SD	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR
Sodium Sulfite	NR	SD	SD	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR
Sodium Tartrate	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD
Sodium Thiosulfate (Hypo)	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD
Soybean Oil	TS	OK	SD	TS	TS	TS	TS	TS	OK	TS	OK	TS	OK	TS	TS	TS	TS	TS
Stannic Chloride	NR	SD	SD	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR
Stannous Chloride	NR	SD	SD	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR
Stearic Acid	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Styrene	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR	NR
Sugar	TS	OK	SD	TS	TS	TS	TS	OK	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS
Sulfamic Acid - 25%	SD	SD	SD	SD	SD	SD	SD	SD	OK	SD	OK	SD	OK	SD	SD	SD	SD	SD
Sulfite Liquor (Paper Industry)	SD	SD	SD	SD	SD	SD	SD	SD	OK	OK	OK	OK	SD	SD	SD	SD	SD	SD
Sulfur Dioxide (Wet)	SD	SD	TS	SD	SD	SD	SD	SD	TS	OK	TS	OK	SD	SD	SD	SD	SD	SD
Sulfur Trioxide (Wet)	SD	SD	TS	SD	SD	SD	SD	SD	TS	OK	TS	OK	SD	SD	SD	SD	SD	SD
Sulfuric Acid - 10%	SD	OK	TS	SD	SD	SD	SD	SD	OK	SD	OK	SD	OK	SD	SD	SD	SD	SD
Sulfuric Acid - 25%	SD	OK	TS	SD	SD	SD	SD	SD	OK	SD	OK	SD	OK	SD	SD	SD	SD	SD
Sulfuric Acid - 50%	SD	SD	TS	SD	SD	SD	SD	OK	SD	OK	SD	OK	SD	SD	SD	SD	SD	SD
Sulfuric Acid - 70%	SD	NR	TS	SD	SD	SD	SD	NR	OK	NR	OK	SD	SD	SD	SD	SD	SD	SD
Sulfuric Acid - 90-98%	NR	NR	NR	NR	NR	NR	NR	NR	OK	NR	OK	NR	NR	NR	NR	NR	NR	NR
Tall Oil	SD	OK	TS	SD	SD	SD	SD	SD	TS	SD	TS	SD	TS	SD	SD	TS	OK	TS
Tartaric Acid	SD	SD	SD	SD	SD	SD	SD	SD	OK	OK	OK	OK	SD	SD	SD	SD	SD	SD
Tetrachloroethane	NR	NR	TS	NR	NR	NR	NR	NR	NR	OK	NR	OK	NR	NR	TS	SD	TS	TS
Tetrachloroethylene	TS	NR	TS	TS	TS	TS	TS	TS	SD	OK	SD	OK	TS	TS	TS	SD	TS	TS
Tetrahydrofuran	TS	NR	TS	TS	TS	TS	TS	TS	TS	OK	TS	OK	TS	TS	TS	SD	TS	TS
Tetrahydrofurfuryl Alcohol	TS	NR	TS	TS	TS	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	SD	TS	TS
Thionyl Chloride	NR	NR	TS	NR	NR	NR	NR	NR	NR	OK	NR	OK	NR	NR	TS	NR	TS	TS
Thionyl Chloride - Water Solution *	TS	NR	TS	TS	TS	TS	TS	TS	NR	OK	NR	OK	TS	TS	TS	SD	TS	TS
Toluol	SD	SD	TS	SD	SD	SD	SD	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	SD
Toluene Sulfonic Acid	NR	NR	TS	NR	NR	NR	NR	NR	SD	OK	SD	OK	NR	NR	TS	SD	TS	TS
Toluidine	NR	NR	TS	NR	NR	NR	NR	NR	TS	OK	TS	OK	NR	NR	TS	SD	TS	TS
Triethylamine	NR	NR	TS	NR	NR	NR	NR	NR	NR	OK	NR	OK	NR	NR	TS	NR	TS	TS
Triethylenetetramine	NR	NR	TS	NR	NR	NR	NR	NR	NR	OK	NR	OK	NR	NR	TS	NR	TS	TS
Triethyl Phosphite	NR	NR	TS	NR	NR	NR	NR	NR	SD	OK	SD	OK	NR	NR	TS	OK	TS	TS
Trichloroacetic Acid - 20%	SD	SD	TS	SD	SD	SD	SD	SD	SD	OK	SD	OK	SD	SD	TS	SD	TS	TS
Trichlorobenzene (1,2,4-)	SD	SD	TS	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD
Trichloroethane	NR	NR	TS	NR	NR	NR	NR	NR	SD	OK	SD	OK	NR	NR	TS	SD	TS	TS
Trichloroethylene	NR	NR	TS	NR	NR	NR	NR	NR	SD	OK	SD	OK	NR	NR	TS	SD	TS	TS
Tricresyl Phosphate - 100%	NR	NR	TS	NR	NR	NR	NR	NR	OK	SD	OK	SD	NR	NR	SD	OK	SD	SD
Trisodium Phosphate (Saturated)	SD	SD	SD	SD	SD	SD	SD	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	SD
Turpentine	NR	NR	TS	NR	NR	NR	NR	NR	SD	SD	SD	SD	NR	NR	SD	SD	SD	SD
Urea Solutions	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Vinegar	SD	SD	SD	SD	SD	SD	SD	SD	SD	OK	SD	OK	SD	SD	OK	OK	OK	OK

OK=Recommended for exposure not to exceed 72 hrs prior to cleaning

SD = Splash/Spillage Daily

NR = Not Recommended

TS = Contact Tech Service Department



**General Polymers**  
High Performance Flooring

Revised 05/2017

	MORTAR SYSTEMS		FasTop (No Topcoat)	SLURRY SYSTEMS				EPOXY / POLYURETHANE COATINGS										
		TPM #115-S4/U1/U4			TRAFFICOTE # 105	CERAMIC CARPET #400	CERAMIC CARPET #554		4090TC FASTOP URETHANE TOPCOAT	3505 STIPPLE EPOXY FLOOR CTG	3525 STATIC CONTROL EPOXY COATING	3555 EPO-FLEX HD COATING	3741 NOVO-FLO SOLVENT/Acid RESISTANT EPOXY COATING	3744 HIGH PERFORMANCE CR EPOXY	3745 SELF-LEVELING EPOXY	4638 HI-SOLIDS POLYURETHANE ENAMEL	4685 POLYCOTE URETHANE	4844 PACE-COTE
Vinyl Chloride	NR	NR		TS	NR	NR			NR	OK	NR	OK	NR	NR	TS	NR	TS	
Water, Distilled & Demineralized	SD	OK		SD	SD	SD			OK	OK	OK	OK	SD	SD	OK	OK	OK	
Water, Deionized	SD	OK		SD	SD	SD			OK	SD	OK	SD	SD	SD	OK	SD	OK	
White Liquor (Paper Industry)	NR	SD		SD	NR	NR			OK	SD	OK	SD	NR	NR	OK	OK	OK	
Wine	TS	OK		SD	TS	TS			TS	SD	TS	SD	TS	TS	TS	TS	TS	
Xylol	NR	SD		TS	NR	NR			SD	SD	SD	SD	NR	NR	SD	SD	SD	
Zinc Plating - Acid Fluoborate	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	OK	OK	OK	
Zinc Plating - Cyanide	SD	SD		SD	SD	SD			TS	OK	TS	OK	SD	SD	OK	OK	OK	
Zinc Plating - Acid Sulfate	NR	SD		SD	NR	NR			TS	SD	TS	SD	NR	NR	OK	OK	OK	